



## TECHNICAL DATA SHEET

### THERMAL METALISED BOPP 30 MICRON

#### Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Extrusion coated thermal lamination film with **METALISED** finish - Mirror effect - Print receptive coating - Both side Corona treated - Low melt adhesive coating inside

Typical Properties					
Graphic Image Films Thermal Metalised BOPP	Property		Unit	Test Method	Value
	Thickness		( µm )	ASTM E 252 84	30
	Yield		m <sup>2</sup> /kg .	ASTM D 4321	36,2
	Unit Weight		g/m <sup>2</sup>	Der - 009	27,6
	Optical Density		%	ASTM 1003 00	2,3
	Wetting Tension	B	Dynes/cm	ASTM D 2578 84	38
		A			38
	C.O.F Film/Film	B/B		ASTM D 1894 90	0,35
	Application Temperature	A	°C		75-100
	Lamination Strength	A	N25/mm		5.0
	A: Adhesive/Metalised Side    B: Printing (Outside)    MD: Machine Direction    TD: Transverse Direction				

**Disclaimer** - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic **Image** Films Ltd.  
 Unit 5, Ridge Way, Crendon Industrial Park,  
 Long Crendon, Bucks, HP18 9BF.  
**T: 01844 208308, F: 01844 208608**  
**Email: info.gif@graphicimagefilms.co.uk**  
**www.graphicimagefilms.co.uk**