



TECHNICAL DATA SHEET

THERMAL SILK 27 MICRON

Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Extrusion coated thermal lamination film with **SILK** finish - Both side Corona treated - Low melt adhesive coating inside - Excellent silky matt finish and good resistance to elongation and tear

Typical Properties					
Graphic Image Films Thermal Silk	Property		Unit	Test Method	Value
	Thickness		(µm)	ASTM E 252	27
	Yield		m ² /kg .	ASTM D 4321	44,44
	Unit Weight		g/m ²		22,5
	Gloss	B	Gardner	ASTM D 2457 45°	17-21
	Wetting Tension	B	Dynes/cm	ASTM D 2578	40
		A			44
	Application Temperature	A	°C		100-120
	A: Adhesive Side B: Silk Side				

Disclaimer - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.
 Unit 5, Ridge Way, Crendon Industrial Park,
 Long Crendon, Bucks, HP18 9BF.
T: 01844 208308, F: 01844 208608
Email: info.gif@graphicimagefilms.co.uk
www.graphicimagefilms.co.uk