



TECHNICAL DATA SHEET

WET MATT 13 MICRON

Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Wet lamination film with **MATT** finish - Both side Corona treated - Excellent natural matt finish - Good Antistat properties - High haze and good contact clarity

Typical Properties					
Graphic Image Films Wet Matt	Property		Unit	Test Method	Value
	Thickness		(µm)	ASTM E 252	13
	Yield		m ² /kg .	ASTM D 4321	85,47
	Unit Weight		g/m ²		11,7
	Gloss	B		ASTM D 2457 45°	6,2
	Wetting Tension	B	Dynes/cm	ASTM D 2578	42
		A			38
	C.O.F Film/Film (Kinetic)	B/B		ASTM D 1894	0,18
	Haze		%	ASTM D 2457	76,4
	Tensile Strength	MD	kg/mm ²	ASTM D 882	11,5
		TD			24,7
	Elongation at Break	MD	%	ASTM D 882	170
		TD			60
	Heat Shrinkage	MD	%	ASTM D 1204	4,3
		TD			0,7
	A: Inside B: Matt Side				

Disclaimer - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.
 Unit 5, Ridge Way, Crendon Industrial Park,
 Long Crendon, Bucks, HP18 9BF.
T: 01844 208308, F: 01844 208608
Email: info.gif@graphicimagefilms.co.uk
www.graphicimagefilms.co.uk