



TECHNICAL DATA SHEET

WET SILK 15 MICRON

Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Wet lamination film with **SILK** finish - Both side Corona treated - Excellent silky matt finish - Good antistat properties

Typical Properties				
Property		Unit	Test Method	Value
Thickness		(µm)	ASTM E 252	15
Yield		m ² /kg .	ASTM D 4321	77,52
Unit Weight		g/m ²		12,9
Gloss	B	Gardner	ASTM D 2457 45°	25-30
Wetting Tension	B	Dynes/cm	ASTM D 2578	40
	A			38
C.O.F Film/Film (Kinetic)	B/B		ASTM D 1894	0,45
Haze		%	ASTM D 1003	32-36
Tensile Strength	MD	kg/cm ²	ASTM D 882	1100-1300
	TD			2400-2700
Elongation at Break	MD	%	ASTM D 882	140-180
	TD			40-60
Heat Shrinkage (120°C, 5min)	MD	%	ASTM D 1204	3,0-5,0
	TD			1,0-3,0
A: Inside B: Silk Side MD: Machine Direction TD: Transverse Direction				

Disclaimer - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.
 Unit 5, Ridge Way, Crendon Industrial Park,
 Long Crendon, Bucks, HP18 9BF.
T: 01844 208308, F: 01844 208608
Email: info.gif@graphicimagefilms.co.uk
www.graphicimagefilms.co.uk